



Exposed treated surface should be protected from rapid drying by use of SprayFilm™, a monomolecular evaporation retardant, or fog spray, wet burlap or white polyethylene. Curing material should not have direct contact with treated surface.

Following the dwell time and temperature guidelines noted above, remove the retarded mortar from the concrete surface using low pressure water spray and stiff brush. Dwell times are approximate and surface should be checked at regular intervals for desired appearance.

After all retarded surface matrix is removed, the clean concrete surface should be protected against physical damage and properly cured.

Polyseal or Polyseal WB are recommended to provide ultimate curing and sealing performance. Polyseal WB is water based and V.O.C. compliant. When applied it has a milky appearance but dries to a clear, hard film.

#### **CLEANUP**

Before material dries and hardens, clean tools and equipment with detergent and warm water.

#### **STORAGE**

Do not allow to freeze. Store tightly closed containers in warm, dry area. Shelf life of properly stored material is one year from date of manufacture.

#### **LIMITATIONS**

- Do not apply at ambient temperatures below 50°F/ 10°C
- Failure to completely remove material from treated surface may result in a slight green discoloration of the concrete

#### **CAUTION**

May cause skin irritation. Do not take internally. Keep out of reach of children.

All label precautions and the MSDS must be read and understood before using this material.

***This Product is Formulated and Labeled for Industrial and Commercial Use Only***

*FOR BEST RESULTS AND SAFEST USAGE, USER IS SPECIFICALLY DIRECTED TO CONSULT THE CURRENT MATERIAL SAFETY DATA SHEET AND PACKAGE LABEL FOR THIS PRODUCT*

*We warrant our products to meet our published specifications and to be free from defects in materials and workmanship to the acceptable quality levels defined in these specifications. If acceptable quality levels are not specified, the acceptable quality levels will be those normally supplied by us for the product. We make no guarantee of the results to be obtained from the use of our products. The determination as to the adaptability of any of our products to the specific needs of the Buyer is solely Buyer's prerogative and responsibility. We are glad to offer suggestions on the use of our products. Nevertheless, there are no warranties given except such expresses warranties offered in connection with the sale of a particular product. Our liability shall be limited to replacement of, or refund of an amount not to exceed the purchase price attributed to, the goods as to which such claim is made. Our selection of one of these alternatives shall be Buyer's exclusive remedy. IN NO CASE SHALL WE BE LIABLE FOR CONSEQUENTIAL OR SPECIAL DAMAGES, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. THE FOREGOING WARRANTIES ARE IN LIEU OF ALL OTHER WARRANTIES, GUARANTEES, CO-CONDITIONS AND REPRESENTATIONS, EITHER EXPRESSED OR IMPLIED, WHETHER ARISING UNDER ANY STATUTE, COMMON LAW, USAGE OR TRADE, COURSE OF DEALING OR OTHERWISE, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.*